



Tork Premium Specialist Cloth Precision Cleaning листовая



Food
contact
approved
certified by
a third party

свойства продукта

| Артикул | Длина до сложения | Ширина до сложения | Длина после сложения | Слои | Печать | Цвет |
|---------|-------------------|--------------------|----------------------|------|--------|-----------|
| 90493 | 38 cm | 27 cm | 14.3 cm | 1 | нет | Бирюзовый |

отгрузочная единица

потребительская единица

| | |
|--------------|---------------|
| Штрих-код | 7310791162027 |
| примеры | 60 |
| материал | Plastic |
| высота | 105 mm |
| ширина | 150 mm |
| длина | 200 mm |
| объем | 3.2 dm3 |
| масса нетто | 480 g |
| масса брутто | 523 g |

паллета

| | |
|-------------------------|---------------|
| Штрих-код | 7322540145632 |
| примеры | 28800 |
| потребительская единица | 480 |
| высота | 1750 mm |
| ширина | 800 mm |
| длина | 1200 mm |
| объем | 1.3 dm3 |
| масса нетто | 230.40 kg |
| масса брутто | 251.04 kg |

транспортная единица

| | |
|-------------------------|---------------|
| Штрих-код | 7310791162034 |
| примеры | 600 |
| потребительская единица | 10 |
| материал | Carton |
| высота | 200 mm |
| ширина | 286 mm |
| длина | 486 mm |
| объем | 27.8 dm3 |
| масса нетто | 4.80 kg |
| масса брутто | 5.23 kg |



ЭКОЛОГИЯ

Content

Chemical pulp, Polyester, Chemicals

Material

Chemical pulp Chemical pulp is produced either from softwood or hardwood. The wood chips are boiled together with chemicals and the major part of the lignin is removed. Chemical pulp is bleached in order to achieve a clean, bright and strong product, but also to increase the hygienic and absorbent qualities. There are two major bleaching methods: ECF (elementary chlorine free) and TCF (totally chlorine free). ECF is based on oxygen, chlorine dioxide and hydrogen peroxide. TCF is based on hydrogen peroxide and ozone. **Polyester** Polyester fibre is produced from terephthalic acid and ethyleneglycol, which react through condensation to polyester resin. The molten resin is spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibre length. **Chemicals** Both functional and process chemicals are used. The functional chemical used is wet strength agent. The wet strength agent is a polyamide (from polyamidine/epichlorohydrin polymer) with a very high affinity to the fibre. Process chemical used is a surfactant.

Production

This product is produced externally in DE.

Destruction

This product is mainly used for industrial processes and hence it will be contaminated with different substances. This will determine how the used product will be destroyed. The product itself is suitable for incineration. Contact local authorities before destruction.